



TYPICAL PROPERTIES

TEST RESULTS

ASTM

SPECIFIC GRAVITY	1.24	(D792)
DUROMETER HARDNESS, 10 SEC. DELAY	80A	(D2240)
TENSILE STRENGTH	2700 PSI	(D412)
ULTIMATE ELONGATION	350%	(D412)
GRAVES TEAR STRENGTH	275 PPI	(D1004)
100% MODULUS	1250 PSI	(D412)
UV RESISTANCE	YES	
LOW TEMPERATURE BRITTLENESS	-36° F / -38° C	(D746)
OPERATING TEMPERATURE	0° F TO 150° F	
FLAMMABILITY	PASS	U.L. 94 V-0

ELECTRICAL PROPERTIES

TEST RESULTS

ASTM

SURFACE RESISTIVITY	1.8 X 10 ¹⁰ (OHM/CM)	(D257)
VOLUME RESISTIVITY	2.2 X 10 ⁹ (OHM/CM)	(D257)
STATIC DECAY RATE	0.19 SECONDS	(FED.STD.101C,M4046)

IMPORTANT: COMPLETE TEST RESULTS FOR OUTGASSING, ANTI-STATIC AND FLAME SPREAD AVAILABLE UPON REQUEST. WE BELIEVE THESE TESTS TO BE RELIABLE AND ACCURATE TO THE BEST OF OUR KNOWLEDGE BUT CANNOT WARRANTY FOR PROCESSES AND APPLICATIONS BEYOND OUR CONTROL.