

**VINYL COMPOUND
 CLEAR ANTI-STATIC**

TYPICAL PROPERTIES	TEST RESULTS	ASTM
SPECIFIC GRAVITY	1.24	(D792)
DUROMETER HARDNESS, 10 SEC. DELAY	80A	(D2240)
TENSILE STRENGTH	2700 PSI	(D412)
ULTIMATE ELONGATION	350%	(D412)
GRAVES TEAR STRENGTH	275 PPI	D1004)
100% MODULUS	1250 PSI	(D412)
UV RESISTANCE	YES	
LOW TEMPERATURE BRITTLINESS	-36° F / -38° C	(D746)
OPERATING TEMPERATURE	0° F TO 150° F	
FLAMMABILITY	PASS	U.L. 94 V-0

ELECTRICAL PROPERTIES	TEST RESULTS	ASTM
SURFACE RESISTIVITY	1.8 X 10 ¹⁰ (OHM/CM)	(D257)
VOLUME RESISTIVITY	2.2 X 10 ⁹ (OHM/CM)	(D257)
STATIC DECAY RATE	0.19 SECONDS	(FED.STD.101C,M4046)

IMPORTANT:

WE BELIEVE THESE TESTS TO BE RELIABLE AND ACCURATE TO THE BEST OF OUR KNOWLEDGE BUT CANNOT WARRANTY FOR PROCESSES AND APPLICATIONS BEYOND OUR CONTROL.