

**VINYL COMPOUND
STANDARD PEBBLE TOP - OPAQUE COLORS**

TYPICAL PROPERTIES	TEST RESULTS	ASTM
SPECIFIC GRAVITY	1.24	(D792)
DUROMETER HARDNESS, 10 SEC. DELAY	80A	(D2240)
TENSILE STRENGTH	2600 PSI	(D412)
ULTIMATE ELONGATION	360%	(D412)
GRAVES TEAR STRENGTH	260 PPI	D1004)
100% MODULUS	1360 PSI	(D412)
UV RESISTANCE	YES	
LOW TEMPERATURE BRITTLINESS	-36° F / -38° C	(D746)
OPERATING TEMPERATURE	0° F TO 150° F	
FLAMMABILITY	PASS	U.L. 94 V-0
FLAMMABILITY	PASS	N.F.P.A. 701

IMPORTANT:

WE BELIEVE THESE TESTS TO BE RELIABLE AND ACCURATE TO THE BEST OF OUR KNOWLEDGE BUT CANNOT WARRANTY FOR PROCESSES AND APPLICATIONS BEYOND OUR CONTROL.