

**VINYL COMPOUND  
STANDARD TRANSLUCENT COLORS**

<b>TYPICAL PROPERTIES</b>	<b>TEST RESULTS</b>	<b>ASTM</b>
SPECIFIC GRAVITY	1.21	(D792)
DUROMETER HARDNESS, 10 SEC. DELAY	83A	(D2240)
TENSILE STRENGTH	2800 PSI	(D412)
ULTIMATE ELONGATION	330%	(D412)
GRAVES TEAR STRENGTH	280 PPI	D1004)
100% MODULUS	1450 PSI	(D412)
UV RESISTANCE	YES	
LOW TEMPERATURE BRITTLINESS	-31° F / -35° C	(D746)
OPERATING TEMPERATURE	0° F TO 150° F	
FLAMMABILITY	PASS	U.L. 94 V-0
FLAMMABILITY	PASS	N.F.P.A. 701

**IMPORTANT:**

WE BELIEVE THESE TESTS TO BE RELIABLE AND ACCURATE TO THE BEST OF OUR KNOWLEDGE BUT CANNOT WARRANTY FOR PROCESSES AND APPLICATIONS BEYOND OUR CONTROL.